



# STONE MASONRY UNIT TEST REPORT

Shouldice stone veneer products are manufactured to comply with all ASTM and CSA standards for manufactured stone. Discover our code compliance policy and how Shouldice Stone exceeds code!

The Shouldice Stone Dimensional Collection is manufactured to exceed Code Standards of the CSA Standard A165 Series-04, the ASTM C 90-13 and ASTM C 55-11 Specifications.

Type	I-25 (I)		DIMENSIONAL STONE UNITS					
	AVG.	IND.	1	2	3	4	5	AVG
Minimum Compressive Strength  MPA (PSI)	25	21.21	37.1	39.1	29.0	30.3	29.3	33.0
	(1900)	(1700)	(5384)	(5667)	(4211)	(4386)	(4253)	(4780)
Oven Dry Mass Density Kg/m3 (lbs/cu ft)	2000 (125)		2110 (132)	2065 (129)	2093 (131)	2106 (132)	2135 (133)	2102 (132)
Maximum Water Absorption Percent by Mass	8		5.9	7.2	6.8	5.1	6.3	6.3

Saturation coefficient means the ratio of the absorption after 24 hours of submersion in cold water to the absorption after 5 h of submersion in boiling water as determined in accordance with CSA Standard CAN3-A82.2

Shouldice Stone  
Collection Exceeds Code